

Product Range

Quality	Main Uses	Construction	Weaving Type	Weight	Certifications
FOREST-582	Petroleum Refineries, Natural Gas Power Plants, Military, Firefighting, Welding, Electric Facilities	Unique blend of; Meta-Aramid, Para Aramid and Anti-Static fibre	Twill	210 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F2 EN ISO 11611 : 2007 Class 1 EN 1149-3 : 2004 (EN 1149-5) Pass EN 61482-1.2 : 2007 Class I (4 kA) EN 14362-1 : 2012 Pass
ETNA	Flammable Gas Filling, Firefighting, Natural Gas Power Plants, Welding, Petroleum Refineries	Unique blend of; Meta-Aramid, Para-Aramid and Anti-Static fibre	Rip-stop	190 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F2 EN ISO 11611 : 2007 Class 1 EN 1149-3 : 2004 (EN 1149-5) Pass EN 14362-1 : 2012 Pass
BROADWAY	Petroleum Refineries, Natural Gas Power Plants, Electric Arc Flash	Unique blend of; Modacrylic, Cotton and Anti-Static fibre	Twill	250 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1 EN 1149-3 : 2004 (EN 1149-5) Pass EN 61482-1.2 : 2007 Class I (4 kA) EN 14362-1 : 2012 Pass
BATTERY	Electri Arc Facilities, Automotive Industry, Petro - Chemical and Natural Gas Plants	Unique blend of; Modacrylic, Viscose FR, Aramid with Anti-Static fibre	Rip-stop	285 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F2 EN ISO 11611 : 2007 Class 1 EN 1149-3 : 2004 (EN 1149-5) Pass EN 61482-1.2 : 2007 Class I (4 kA) EN 14362-1 : 2012 Pass
SAHARA	Wildland Firefighters, Search & Rescue Teams	Unique blend of; Para-Aramid, Meta-Aramid and Anti-Static fibre	Twill	190 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1 EN 1149-3 : 2004 (EN 1149-5) Pass
ITALY	Firefighting, Flammable Gas Filling, Military, Petro-Chemical, Automotive Industry	Unique blend of; Meta-Aramid, Para-Aramid and Anti-Static fibre	Twill	190 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F1 EN 1149-3 : 2004 (EN 1149-5) Pass EN 14362-1 : 2012 Pass
WORKER-150	Shirting for Petroleum Refineries, Oil Station Workers, Natural Gas Power Plants	Unique blend of; Lenzing FR, Para-Aramid, Polyamid and Anti-Static fibre	Rip-stop	150 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F1 EN 1149-3 : 2004 (EN 1149-5) Pass
WORKER-195	For Hot Climates, Fuel-Oil Stations, Tanker Drivers, Petroleum and Natural Gas Plants, Iron&Steel	Unique blend of; Lenzing FR, Para-Aramid, Polyamid and Anti-Static fibre	Rip-stop	195 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F1 EN 1149-3 : 2004 (EN 1149-5) Pass
WORKER-260	Welding, Iron&Steel, Glass Industry, Automotive Industry, Mining	Unique blend of; Lenzing FR, Para-Aramid, Polyamid and Anti-Static fibre	Twill	260 gr/mt ²	EN ISO 11612 : 2008 A1-A2-B1-C1-F1 EN ISO 11611 : 2007 Class 1 EN 1149-3 : 2004 (EN 1149-5) Pass EN 14362-1 : 2012 Pass
CONDOR	Linings of Turn-Out Suits and Winter Jackets	Unique blend of; Meta-Aramid and Lenzing FR fibre	Plain	110 gr/mt ²	EN ISO 14116 : 2008 Index 3 / 5H / 60

Country	Tel.	Country	Tel.
Bulgaria	+ 359 (2) 976 77 41 / 49	Romania	+ 40 21 316 7229
Czech Republic	+ 420 (461) 619853	Russia	+ 7495 5105 184
Egypt	+ 2015 372 294	Slovakia	+ 421 2 63537713
France	+ 33 3 20 10 63 63	South Africa	+ 27 (31) 736 2171
Germany	+ 49 (0) 771 609 0	Spain	+ 34 93 290 84 95
Hungary	+ 361 399 4100	Tunisia	+ 216 71 545 870
Italy	+ 39 02 636151	Turkey	+ 90 216 425 8810
Morocco	+ 212 5 2266 2550	Ukraine	+38 (044) 586 49 68
Poland	+ 48 42 2540400	United Kingdom	+ 44 845 603 0150
Portugal	+ 351 227845609		

akdoku
protect

made with
COATS
Coats
Flamepro

akdoku
protect


made with
COATS
Coats
Flamepro

CONDOR
Lining for Firefighter Suits



Main Uses: Linings of Turn-Out Suits and Winter Jackets

- Condor is designed as a lining fabric for turn-out suits to keep the skin away from the heat and flame. It has inherent heat and flame resistance.
- It is flexible, thin and super-light in weight. Its special blend helps to keep the body dry and cool in a hot working environment.
- The smooth surface and high tenacity make it easy to use.



CONDOR

Lining for Firefighter Suits



CERTIFICATIONS	STANDARDS
EN ISO 14116 : 2008	INDEX 3 / 5H / 60



Test	Method	Result
ELECTRIC ARC TEST	EN 61482-1.2 Class 1 (4 kA)	N/A
FLAME SPREAD FABRIC AFTER WASH A1	EN 15025 Met.A:2002	N/A
FLAME SPREAD FABRIC ORIGINAL A1	EN 15025 Met.A:2002	N/A
FLAME SPREAD FABRIC AFTER WASH A2	EN 15025 Met.B:2002	N/A
FLAME SPREAD FABRIC ORIGINAL A2	EN 15025 Met.B:2002	N/A
RADIANT HEAT (AFTER WASHING FABRIC 20KW)	EN ISO 6942:2002 Met.B	N/A
CONVECTIVE HEAT (AFTER WASHING FABRIC 80KW)	ISO 9151:1995 Pto.B	N/A
CONTACT HEAT AFTER WASHING	ISO 12127 Pto.F	N/A
HEAT RESISTANCE 180°C	ISO 17493	PASS
HEAT RESISTANCE	EN ISO 14116 Index 3	Index 3/5H/60
TEAR STRENGTH AFTER WASH.	EN ISO 13937-2:2001	Warp : 15 N Weft : 12 N
TENSILE STRENGTH AFTER WASH.	EN ISO 13934-1:1999+ERRATUM 2000	Warp : 350 N Weft : 320 N
BURSTING STRENGTH	EN ISO 13938-2: Hydrostatic Method	N/A
SMALL MOLTEN METAL SPLASHES AFTER WASHING	ISO 9150	N/A
ELECTRICAL INSULATION AFTER WASHING	EN 1149-2:1998	N/A
CHARGE DECAY AFTER WASHING	EN 1149-3:2004 Met.2	N/A
DETERMINATION OF FORBIDDEN AZO COLORANTS	EN 340:2004; EN 14362-1:2004/AC:2005	N/A
DIMENSIONAL STABILITY FABRIC FOR EACH FABRIC	EN ISO 5077:2008 + ERRATUM:2008	Warp : - 2,0 % Weft : - 2,0 %
COLOUR FASTNESS TO WASHING	EN ISO 105-C06:1997 Method C2S (@ 60 ° C)	4
COLOUR FASTNESS TO DRY CLEAN	EN ISO 105-D01:1995	4
COLOUR FASTNESS TO RUB FASTNESS	EN ISO 105-X12:1995	Dry: 4 Wet: 2-3
COLOUR FASTNESS TO PERSPIRATION	EN ISO 105-E04: 2013	Acid: 4 Alkaline: 4
DETERMINATION OF PH VALUE	EN 3071:06	N/A
MARTINDALE ABRASION	EN 12947-2:1999(9 kPA)	> 5.000
PILLING RESISTANCE (2000 rubs) (After 1 washing @ 60 ° C)	EN ISO 12945-2:2001	2-3

CONDOR

Lining for Firefighter Suits



FABRIC CONSTRUCTION	Unique blend of; Meta-Aramid and Lenzing FR fibre
WEIGHT	110 gr/ mt ²
WEAVING TYPE	Plain
USABLE WIDTH	150 cm

Main Uses: Linings of Turn-Out Suits and Winter Jackets

Please contact your sales executive for further information.